

ASBESTOS-CONTAINING BUILDING MATERIALS RE-ASSESSMENT REPORT

I. E. Weldon Secondary School

24 Weldon Road
Lindsay, Ontario

Presented to:

Trillium Lakelands District School Board

Box 420, County Road 36
Lindsay, Ontario
K9V 4S4

Attention: Daniel Whalen

September 2024

Maple Project No. 21700-48

Executive Summary

2024 Asbestos-Containing Building Materials Re-Assessment Report

Maple Project	School Name	Address
21124-48	I.E. Weldon Secondary School	24 Weldon Road, Lindsay, Ontario

Maple Environmental Inc. was retained by Trillium Lakelands District School Board to perform a re-assessment of known asbestos-containing building materials within the subject building.

The findings and recommendations of the current assessment are summarized below. Please refer to the main body of the report for details.

FINDINGS

Asbestos-containing materials (ACM) identified within the building at the time of the assessment are as follows:

ASBESTOS BUILDING MATERIALS SUMMARY								
MATERIAL		ASBESTOS			FRIABILITY			Remedial Work Required
		Yes	No	Suspect	Friable	Non-Friable	Potentially	
Sprayed Fireproofing			X		X			NO
Textured Finish			X		X			NO
Mechanical Insulations	Pipe Fittings		X		X			NO
	Pipe Straight		X		X			NO
	Ductwork		X		X			NO
	Mechanical Equip.		X		X			NO
Ceiling Tiles			X				X	NO
Vinyl Sheet Flooring			X				X	NO
Vinyl Floor Tiles			X			X		NO
Asbestos Cement (Transite)				X		X		NO
Plaster				X			X	NO
Drywall Joint Compound		X				X		No
Other (roofing, caulking, etc.)				X		X		NO

Please refer to Room by Room Inventory in Appendix I to view location, quantities, and condition of ACM observed within the building at the time of the assessment.

Executive Summary

2024 Asbestos-Containing Building Materials Re-Assessment Report

RECOMMENDATIONS

As asbestos-containing materials were found to be present within the building, Ontario Regulation 278/05 requires that the Trillium Lakelands District School Board's Asbestos Management Plan must apply to this building. In addition, an annual re-assessment of all ACM must be performed.

All asbestos-containing materials identified within the building were observed to be in GOOD condition and therefore no immediate recommendations are warranted.

General Statement

The Executive Summary must be read in conjunction with the main body of this report.

TABLE OF CONTENTS

EXECUTIVE SUMMARY	<i>i</i>
1.0 INTRODUCTION	1
2.0 APPLICABLE ONTARIO REGULATIONS.....	1
2.1 ONTARIO REGULATION 278/05 (ASBESTOS)	1
2.2 ONTARIO REGULATION 347	2
3.0 SURVEY SCOPE AND METHODOLOGY.....	2
3.1 INVENTORY METHODOLOGY.....	3
3.2 ASBESTOS ASSESSMENT CRITERIA	3
3.3 LIMITATIONS AND OMISSIONS FROM SCOPE	4
3.4 SAMPLING STRATEGY AND ANALYTICAL METHODS	5
3.5 DRAWINGS.....	6
4.0 INVENTORY FINDINGS.....	6
4.1 SPRAYED FIREPROOFING (FRIABLE)	7
4.2 THERMAL MECHANICAL INSULATION (FRIABLE)	7
4.3 TEXTURE FINISH (FRIABLE)	7
4.4 ACOUSTIC CEILING TILES (POTENTIALLY FRIABLE).....	7
4.5 VINYL SHEET FLOORING (POTENTIALLY FRIABLE)	8
4.6 VINYL FLOOR TILE (NON-FRIABLE).....	8
4.7 ASBESTOS CEMENT PRODUCTS "TRANSITE" (NON-FRIABLE)	8
4.8 DRYWALL JOINT COMPOUND (DJC)	8
4.9 PLASTER.....	8
5.0 RECOMMENDATIONS	8
5.1 GENERAL RECOMMENDATIONS	8
5.2 SPECIFIC RECOMMENDATIONS	9
6.0 LIMITATIONS.....	9
 APPENDIX I	 ROOM-BY-ROOM ASBESTOS INVENTORY
APPENDIX II	DRAWINGS
APPENDIX III	POTENTIAL ASBESTOS-CONTAINING MATERIAL IDENTIFICATION SHEET

1.0 INTRODUCTION

MAPLE Environmental Inc. ("MAPLE") was retained by the Trillium Lakelands District School Board (TLDSB) to perform a re-assessment of known asbestos-containing building materials within all TLDSB schools where asbestos was previously confirmed to be present (by others).

The assessment was completed in accordance with the requirement of Ontario Regulation 278/05 to complete a re-assessment on an annual basis.

The following report presents the findings and recommendations of the assessment for the specific building listed.

SUMMARY OF BUILDING INFORMATION	
School Name:	I.E. Weldon Secondary School
Building Address:	24 Weldon Road, Lindsay, Ontario
Number of Floors:	2 (no basement)
Approximate Square Footage:	140,000
Assessed by:	Richards Reboks
Assessment Date:	July 22, 2024

2.0 APPLICABLE ONTARIO REGULATIONS

Applicable Ontario Regulations for each of the materials included in the investigation are briefly described below.

2.1 Ontario Regulation 278/05 (Asbestos)

The Ontario Ministry of Labour Regulation 278/05 requires a detailed asbestos inventory be performed in all buildings where friable and non-friable asbestos-containing materials (ACM) are present. The inventory must be available at the work place and must identify the type and location of asbestos-containing materials on a room-by-room basis, where necessary.

Each individual building report prepared by MAPLE meets or exceeds the requirements for an asbestos survey under Ontario Regulation 278/05.

Ontario Regulation 278/05 applies to buildings with regards to maintenance, renovation or demolition work where ACM is present and may be disturbed. The regulation requires all buildings where asbestos is known to be part of the building materials to implement an Asbestos Management Program

(AMP). TLDSB has prepared and maintains an AMP of which the current Re-Assessment report is part of.

2.2 Ontario Regulation 347

Ontario Regulation 347 applies to the transport of waste from the location of generation to a landfill site authorized to receive specific wastes. The regulation also prescribes procedures on how the specific wastes are to be handled at the landfill site.

The major requirements of the building owner and the person(s) removing the waste are to ensure that:

- The waste is appropriately packaged and labelled;
- The transport vehicle is appropriately placard; and
- The waste is to be transported as directly as possible to the landfill site once it leaves the site.

Some wastes require the Owner to register a Generator (of waste) number and many wastes require classification that can restrict or even prohibit their disposal in landfill.

It is important to note that the building owner can be held responsible for the waste until the waste disposal site accepts it.

3.0 SURVEY SCOPE AND METHODOLOGY

The surveys were performed on a Room-by-Room basis within each building included in the scope of the assessment where asbestos was previously identified (by others).

The scope of the surveys included all friable and major non-friable materials suspected to contain asbestos. The term friable is applied to a material that can be readily reduced to dust or powder by hand or moderate pressure. Asbestos materials that are friable have a much greater potential to release airborne asbestos fibres when disturbed.

Typical friable asbestos materials include; sprayed fireproofing or thermal insulation, textured (stippled) plaster, and thermal mechanical insulation. Typical non-friable materials include: asbestos cement (transite) products, caulking, vinyl floor tiles, asbestos textiles and gaskets. Additional materials such as ceiling tiles and drywall joint compounds are classified as non-friable, but because of their ability to release dust when disturbed they are considered as "potentially friable" for the purpose of this report.

3.1 Inventory Methodology

In order to determine the location of the materials included in the assessment, each room or area was entered where practical (i.e.: where access was possible without the demolition of walls, roof or ceilings or destruction of flooring) where asbestos materials were previously identified. An investigation of areas of the building where asbestos was not previously identified was not included in the scope of the current project.

Representative views were made above accessible suspended ceiling systems. Drywall or plaster ceilings were accessed via existing ceiling access panels only. The inventory did not include destructive testing of building systems or finishes to observe possible hidden conditions.

3.2 Asbestos Assessment Criteria

The recommendations and suggestions made as part of this report with respect to asbestos have taken into consideration the condition and accessibility of the asbestos-containing material as well as other factors such as water damage, vibration, air movement, and general activities in the area.

Where ACM is found to be in GOOD condition and not likely to deteriorate or fall, the general recommendation would be to re-evaluate the condition of the material on an annual basis (required by Regulation 278/05). This recommendation can be subject to change if the material is located in a manner that persons untrained in asbestos awareness could physically damage it.

Where the ACM is found to be damaged (i.e. FAIR or POOR condition), a recommendation to have the material cleaned-up, repaired, removed, enclosed, or encapsulated is offered. The recommendation will also indicate which asbestos procedure should be used to perform the remedial work (i.e. Type 1, Type 2, Type 3, or Glove Bag Removal Methods).

In each area or room inventoried, the quantity, condition (GOOD, FAIR, or POOR) and accessibility (A, B, C, D or E) of each suspect material was recorded.

The definitions for condition and accessibility items are as follows:

GOOD	Material is intact with no visible signs of damage.
FAIR	Material is visibly damaged but can be repaired.
POOR	Material is damaged beyond repair and likely needs to be removed.
Access A	Accessible to all occupants of the building.

- | | |
|-----------------|--|
| Access B | Accessible to Maintenance personnel without the use of a ladder (i.e. Mechanical Room, pipe chase etc.). |
| Access C | Accessible to Maintenance personnel with the use of a ladder and is exposed to view without removing building components. |
| Access D | Accessible to Maintenance personnel with the use of a ladder and is concealed from viewing due to a building component (i.e. above a removable ceiling). |
| Access E | Not accessible without demolition of a building component (i.e. above a fixed ceiling system). |

The asbestos related information collected during the previous assessments was confirmed and the room-by-room data updated to reflect the current information.

3.3 Limitations and Omissions from Scope

Due to the nature of building construction, some limitations exist in regards to the possible thoroughness of any building materials inventory. The field observations, measurements, and analysis are considered sufficient in detail and scope to form a reasonable basis for the findings presented in this report. MAPLE warrants that the findings and conclusions contained herein have been made in accordance with generally accepted evaluation methods in the industry and applicable regulations at the time of the performance of the inventory.

It is possible that conditions may exist which could not be reasonably identified within the scope of the inventory or which were not apparent during the site investigation. MAPLE believes that the information collected during the inventory period concerning the property is reliable. No other warranties are implied or expressed.

In addition, during a standard asbestos assessment, performed for the purposes of regulatory compliance, it is industry practice to exclude some non-friable materials in the inventory. Examples of such assumptions include; elevator brakes, roofing felts and mastics, high voltage wiring, mechanical packing and gaskets, underground services or piping, fire-doors, window caulking, levelling compound, and/or materials used in operating equipment. As such, these materials were not sampled at the time of this survey and where present are assumed to be asbestos containing until proven otherwise.

3.4 Sampling Strategy and Analytical Methods

As the majority of materials were previously sampled by others, the requirement for sampling during the current survey was limited. Where samples were collected, they conformed to the criteria outlined below and in compliance with O. Reg. 278/05.

A small volume of the material was removed either from a damaged section or cut out of intact material and then repaired by sealing with tape to prevent the release of fibres. The collected samples were placed in plastic bags, sealed and labelled and then sent to an independent laboratory for analysis. To ensure quality results, the independent laboratory chosen is NVLAP accredited and successfully participates in an "Asbestos Proficiency Analytical Testing Program" and as such, these laboratories are responsible for their findings.

The collection of samples was performed in accordance with regulatory sampling requirements and with sufficient frequency to obtain a general pattern of asbestos use within the building. Due to building renovations or modifications that have occurred, the consistency of the application of asbestos materials may not be uniform throughout the entire building. It is important to note that without sampling every wall, pipe section, ceiling tile etc. it is not possible to identify the possible asbestos content in every material present in the building. For this reason, materials similar in appearance to those sampled elsewhere in the building were visually identified as being homogeneous and thus are assumed to be composed of the same material, thus additional sampling is not required.

In accordance with Reg. 278/05, samples were collected at the following frequency.

Material Type	No. Samples
Sprayed Fireproofing	Up to 7
Texture Coat	Up to 7
Pipe Fitting Insulation	3
Pipe Straight Insulation	3
Ductwork Insulation	3
Ceiling Tiles	3
Vinyl Sheeting Flooring	3
Vinyl Floor Tile	3
Plaster Finishes	Up to 7
Drywall Compound	Up to 7

An independent NVLAP accredited laboratory, was used to analyse the collected samples. Analysis was performed following the Code of Practice for the identification of asbestos in bulk material, as detailed in Ontario Regulation 278/05. Bulk samples were analysed using the Polarized Light Microscopy ("PLM") Technique with Dispersion Staining. The identification of asbestos fibre in bulk material is based on a collective set of parameters dependent on the unique shape and crystallographic properties of each fibre as viewed through the microscope. This method is useful for the qualitative identification of asbestos and the semi-quantitative determination of asbestos content in bulk materials expressed as a percent of projected area. The method identifies types of asbestos and also measures percent of asbestos as perceived by the analyst in comparison to standard area projections or trained experience.

Given the composition of some vinyl floor products, the PLM analysis method is often prone to yielding false negative analysis results. Therefore it may be prudent that the Transmission Electron Microscopy (TEM) analysis method be used to determine the asbestos content in the vinyl floor products, if negative results are obtain from the laboratory analysis.

3.5 Drawings

Drawings provided for each building indicate the following (where present):

- ◇ Location Numbers (reference to Room-by-Room asbestos data)
- ◇ Asbestos-Containing Sprayed Fireproofing
- ◇ Asbestos-Containing Texture Finishes
- ◇ Asbestos-Containing Ceiling Tiles
- ◇ Asbestos-Containing Flooring Materials
- ◇ Presence of Asbestos-Containing Mechanical Insulations will not be specifically indicated on the drawings; however, a general statement regarding the presence of ACM mechanical insulations, where present, has been indicated on the drawings.
- ◇ Presence of asbestos-containing drywall joint compound and hard plaster will not be specifically identified on the drawings; however, a general statement regarding the presence of these ACM materials, where present, has been indicated on the drawings.

4.0 INVENTORY FINDINGS

The following is a brief discussion of the extent to which Asbestos-Containing Materials (ACM) was identified in the building. The discussion is organized under the headings of materials that are generally suspected of containing asbestos. Refer to the Room-by-Room Survey Inventory in Appendix I for a detailed description and location of all ACM.

Destructive testing was not conducted and as such some areas within the building were not accessible for an assessment (i.e. above solid ceilings, behind walls). Access for viewing within wall and ceiling cavities was not always possible. Suspect asbestos materials may be present within ceiling and wall cavities that were not identified in this report. This comment is particularly important for materials such as mechanical insulation. Caution should be taken when demolishing solid wall finishes within the building.

4.1 Sprayed Fireproofing (Friable)

No asbestos-containing sprayed fireproofing was observed in the building. The sprayed fire proofing previously identified in several locations was determined to be non-asbestos.

4.2 Thermal Mechanical Insulation (Friable)

No asbestos-containing mechanical insulations are present in the building. It is important to note that mechanical systems may be present within walls and ceiling cavities or pipe chases that were not accessible during this assessment. The presence of ACM mechanical insulations in these locations should be suspected.

Pipe Systems:

Pipe Fittings, where insulated are insulated with non-asbestos fibreglass and/or armaflex materials.

Pipe Straights, where insulated are insulated with non-asbestos fibreglass and/or armaflex materials.

Ductwork:

Duct systems were either insulated with non-asbestos fibreglass or were un-insulated.

Mechanical Equipment:

Mechanical equipment was observed to be externally un-insulated.

4.3 Texture Finish (Friable)

No asbestos-containing texture finishes were identified to be present within the building.

4.4 Acoustic Ceiling Tiles (Potentially Friable)

No asbestos-containing ceiling tiles were identified to be present within the building.

4.5 Vinyl Sheet Flooring (Potentially Friable)

No asbestos-containing vinyl sheet flooring was identified to be present within the building.

4.6 Vinyl Floor Tile (Non-Friable)

No asbestos-containing vinyl floor tiles were identified to be present within the building.

4.7 Asbestos Cement Products "Transite" (Non-Friable)

Suspect asbestos-containing transite is present in the form of rain water leaders and roof drains within Room 164 (eBase 116) as well as panels on the building exterior. It should be noted that transite pipes were identified in areas not previously identified. Maple conducted some level of additional investigation for transite but did not enter all rooms in the building. Caution should be taken when performing work on rain water leaders. All transite was found to be in GOOD condition. Refer to the Room-by-Room Inventory in Appendix I for details regarding location and quantity.

4.8 Drywall Joint Compound (DJC)

Previous sample results indicated drywall joint compound sampled at the Site contains asbestos. All drywall should be assumed to contain asbestos unless testing in specific areas indicates otherwise. The drywall was found to be in GOOD condition.

4.9 Plaster

While previous sample results indicated all plaster finishes sampled at the Site does not contain asbestos, note that the concentration of asbestos within plaster is historically known to be potentially inconsistently distributed. Further, it is possible that various phases of construction and renovations have occurred at the Site. Therefore, the number of samples previously collected may not be representative of all plaster finishes in the building.

5.0 RECOMMENDATIONS

5.1 General Recommendations

Due to the presence of ACM within the building, TLDSB must maintain their existing Asbestos Management Program for this property.

A re-assessment of known ACM is to be conducted at least once annually.

It is important to note that due to the presence of solid walls and ceiling systems, ACM may be present in concealed locations not identified in this report.

Asbestos-containing drywall joint compound is present within the building. Removal or disturbance of less than 1 m² of this material will require the use of Type 1 Asbestos procedures, and the disturbance of greater than less than 1 m² will require Type 2 Asbestos procedures.

Removal or disturbance of transite cement products requires the use of Type 1 Asbestos procedures (provided no power tools are used and the material is wetted). If power tools are required Type 3 Asbestos procedures need be applied.

Materials suspected of containing asbestos should be sampled prior to disturbance. Suspect materials include; drywall joint compound, plaster, roofing materials, caulking, etc. unless previously confirmed to contain asbestos.

5.2 Specific Recommendations

All ACM was identified in GOOD condition. As such no immediate recommendations are warranted at this time.

6.0 LIMITATIONS

Due to the nature of building construction some limitations exist as to the possible thoroughness of the subject investigation. The field observations are considered sufficient in detail and scope to form a reasonable basis for the findings presented in this report. MAPLE warrants that the findings and conclusions contained herein have been made in accordance with generally accepted evaluation methods in the industry and applicable regulations at the time of the performance of the assessment.

It is possible that conditions may exist which could not be reasonably identified within the scope of the investigation or which were not apparent during the site investigation. MAPLE believes that the information collected during the investigation period concerning the property is reliable. No other warranties are implied or expressed.

Information provided by Maple is intended for Client use only. Any use by a third party, of reports or documents authored by Maple, or any reliance by a third party on or decisions made by a third party based on the findings described in said documents, is the sole responsibility of such third parties. Maple accepts no responsibility for damages suffered by any third party as a result of decisions made or actions conducted.

The liability of Maple or its staff will be limited to the lesser of the fees paid or actual damages incurred by the Client. Maple will not be responsible for any consequential or indirect damages. Maple will only be liable for damages resulting from negligence of Maple; all claims by the Client shall be deemed relinquished if not made within two years after last date of services provided.

Please contact Maple Environmental Inc. at (905) 257-4408 for inquiries regarding this project.

Sincerely,

MAPLE ENVIRONMENTAL INC.
Environment, Health and Safety Consultants

Prepared By:



Richards Reboks
Senior Project Technologist

Reviewed By:



Kyle Prosser
Senior Project Manager

APPENDIX I
ROOM-BY-ROOM ASBESTOS INVENTORY



STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY																	
RF: Roof WN: Window FL: Floor CL: Ceiling WL: Wall DK: Deck			B/J: Beams/Joists CB: Chalkboard PI: Pipe DT: Duct BL: Bolter MC: Mechanical			A: All occupants of the facility B: Maintenance staff without a ladder C: Maintenance staff with a ladder, exposed to view without moving building components D: Maintenance staff with a ladder, concealed from view by building components E: No access without demolition or removal of fixed building components or systems			ACM: Asbestos Containing Material CT: Ceiling Tile Analyzed DJC: Drywall Joint Compound FTG: Fitting LF: Linear Feet MIX: Mastic CONDITION G: Good F: Fair P: Poor			N/A: Not Applicable N/A/NZ: Not Analyzed N/D: None Detected PI-AC: Pipe Insulation - Aircell PI-PC: Pipe Insulation-Pairing Cement PI-MIX: Pipe Insulation-Capsule			PL: Plaster RM: Roofing Materials SFP: Sprayed Fireproofing SF: Square Feet TF: Texture Finish			TB: Transite Board TP: Transite Pipe VI: Vermiculite Insulation VFT: Vinyl Floor Tile			VSF: Vinyl Sheet Flooring VIC: Visually Consistent w/ Other Sampled Material WC: Window Caulking		
Floor #	Room #	Room name	Has ACM	Friable	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes						
1	101A	Stairs 2	No	Yes	WL	TF		N/D	-	-	40-BS-01C			-									
1	101A	Stairs 2	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	101A	Stairs 2	No	No	CL	CT		N/D	-	-	VIC:40-BS-07			-									
1	102	Lobby	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	102	Lobby	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			C			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	102	Lobby	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103	Main Office	No	No	FL	VFT	1	N/D	-	-	VIC:40-BS-05			-									
1	103	Main Office	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103	Main Office	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103	Main Office	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103A	Room 01	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103A	Room 01	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103A	Room 01	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103B	Room 02	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103B	Room 02	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103B	Room 02	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103C	Room 03	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103C	Room 03	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103C	Room 03	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103D	Room 04	No	No	FL	VFT	1	N/D	-	-	VIC:40-BS-05			-									
1	103D	Room 04	No	Yes	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103D	Room 04	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103D	Room 04	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103E	Room 05	No	No	FL	VFT	6	N/D	-	-	VIC:40-BS-11			-									
1	103E	Room 05	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103E	Room 05	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103E	Room 05	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	103F	Room 06	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	103F	Room 06	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	103F	Room 06	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	104	Hallway H10	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	104	Hallway H10	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	104	Hallway H10	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105	Room G (Guidance)	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105	Room G (Guidance)	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105	Room G (Guidance)	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105A	Room G1	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105A	Room G1	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105A	Room G1	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105B	Room G2	No	No	FL	VFT	6	N/D	-	-	VIC:40-BS-11			-									
1	105B	Room G2	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105B	Room G2	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105B	Room G2	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105C	Room G3	No	Yes	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105C	Room G3	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105C	Room G3	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105D	Room G4	No	No	FL	VFT	6	N/D	-	-	VIC:40-BS-11			-									
1	105D	Room G4	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105D	Room G4	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105D	Room G4	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105E	Room G5	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105E	Room G5	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105E	Room G5	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105F	Room G6	No	No	FL	VFT	6	N/D	-	-	VIC:40-BS-11			-									
1	105F	Room G6	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105F	Room G6	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105F	Room G6	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105G	Room G7	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105G	Room G7	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105G	Room G7	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105H	Room G8	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105H	Room G8	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105H	Room G8	Yes	No	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105I	Room G9	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105I	Room G9	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105I	Room G9	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105J	Room G10	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105J	Room G10	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105J	Room G10	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105K	Room G12	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	VIC:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105K	Room G12	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105K	Room G12	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105L	Room G13	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	40-BS-03G			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105L	Room G13	No	No	CL	CT	1	N/D	-	-	VIC:40-BS-07			-									
1	105L	Room G13	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105M	Room 104 (Staff WS)	Yes	No	CL	DJC		0.75% -1% Chrysotile	80	SF	G	VIC:40-BS-03			C		Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105M	Room 104 (Staff WS)	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	105N	Room 105 (Staff WS)	Yes	No	CL	DJC		0.75% -1% Chrysotile	80	SF	G	VIC:40-BS-03			C		Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	105N	Room 105 (Staff WS)	No	Yes	ST	SFP		N/D	-	-	VIC:40-BS-21			-									
1	107	Room 102 (Washroom)	Yes	No	CL	DJC																	



STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY											
RF: Roof WN: Window FL: Floor CL: Ceiling WL: Wall DK: Deck	BJ: Beams/Joints CB: Chalkboard PI: Pipe DT: Duct ML: Boiler MC: Mechanical	A: All occupants of the facility B: Maintenance staff without a ladder C: Maintenance staff with a ladder, exposed to view without moving building components D: Maintenance staff with a ladder, concealed from view by building components E: No access without demolition or removal of fixed building components or systems	ACM: Asbestos Containing Material CT: Ceiling Tile DJC: Drywall Joint Compound FTG: Fitting LF: Linear Feet JAL: Jalousie CONDITION G: Good F: Fair P: Poor			N/A: Not Applicable N/A/NZ: Not Analyzed ND: None Detected PI/AC: Pipe Insulation - Aircell PI/PC: Pipe Insulation-Pairing Cement PI/M: Mastic			PL: Plaster RM: Roofing Materials SFP: Sprayed Fireproofing SF: Square Feet TF: Texture Finish			TB: Transite Board TP: Transite Pipe VI: Vermiculite Insulation VFT: Vinyl Floor Tile			VSF: Vinyl Sheet Flooring VC: Visually Consistent w/ Other Sampled Material WC: Window Caulking		
Floor #	Room #	Room name	Has ACM	Prohibit	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes
1	110A	Room 153F	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	110A	Room 153F	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	110B	Room 153G	No	No	FL	VFT	5	N/D	-	-	V/C:40-B5-10	-	-	-	-	-	-
1	110B	Room 153G	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	110B	Room 153G	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	110B	Room 153G	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	110C	Room 153I	-	-	-	-	-	-	-	-	-	-	-	-	-	-	ACM and/orPACM not observed
1	110D	Room 153H	-	-	-	-	-	-	-	-	-	-	-	-	-	-	ACM and/orPACM not observed
1	111	Room 157	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-	-
1	111	Room 157	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	111	Room 157	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	111	Room 157	No	Yes	ST	SFP	-	N/D	-	-	40-B5-21A	-	-	-	-	-	-
1	111A	Room 157 A	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-	-
1	111A	Room 157 A	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	111A	Room 157 A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	111A	Room 157 A	No	Yes	ST	SFP	-	N/D	-	-	40-B5-21C	-	-	-	-	-	-
1	112	Room 165	-	-	-	-	-	-	-	-	-	-	-	-	-	-	ACM and/orPACM not observed
1	112A	Room 153J	-	-	-	-	-	-	-	-	-	-	-	-	-	-	ACM and/orPACM not observed
1	113	Hallway H3	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	113	Hallway H3	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	113	Hallway H3	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	115	Room 163	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	115A	Room 163A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	115B	Room 163B	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	116	Room 164	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	116	Room 164	No	Yes	PI	TP	-	ACM ASSUMED	8 LF	G	N/S	-	D	-	-	-	-
1	116A	Room 164 A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	116A	Room 164 A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	116B	Room 164B	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	117	Room 166 (Girls WR)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	117	Room 166 (Girls WR)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	118	Room 167 (Boys WR)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	118	Room 167 (Boys WR)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	119	Room 168 (Custodian Rod)	No	No	FL	VFT	5	N/D	-	-	40-B5-10B,C	-	-	-	-	-	-
1	119	Room 168 (Custodian Rod)	No	No	FL	VFT	6	N/D	-	-	V/C:40-B5-11	-	-	-	-	-	-
1	119	Room 168 (Custodian Rod)	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	119	Room 168 (Custodian Rod)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	120	Room 170	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	40-B5-03C	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	120	Room 170	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	120	Room 170	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	121	Room 172	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	121	Room 172	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	121A	Room 172 A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	121A	Room 172 A	No	Yes	SFP	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	121B	Room 172 B	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	121B	Room 172 B	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	121C	Room 172 C	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	122	Room 174	No	No	FL	VFT	6	N/D	-	-	40-B5-11C	-	-	-	-	-	-
1	122	Room 174	No	Yes	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	122	Room 174	No	No	CL	CT	2	N/D	-	-	V/C:40-B5-16	-	-	-	-	-	-
1	122	Room 174	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	122A	Room 174 A	No	No	FL	VFT	6	N/D	-	-	V/C:40-B5-11	-	-	-	-	-	-
1	122A	Room 174 A	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	122A	Room 174 A	No	No	CL	CT	2	N/D	-	-	V/C:40-B5-16	-	-	-	-	-	-
1	122A	Room 174 A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	123	Hallway H2	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	123	Hallway H2	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	123	Hallway H2	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	124	Stairs 3	No	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	124	Stairs 3	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	125	Room 176	No	No	CL	CT	2	N/D	-	-	V/C:40-B5-16	-	-	-	-	-	-
1	125	Room 176	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	126	Room 178	No	No	CL	CT	2	N/D	-	-	V/C:40-B5-16	-	-	-	-	-	-
1	126	Room 178	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	127	Room 173 (Boys CR)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	127	Room 173 (Boys CR)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	128	Hallway H1	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	128	Hallway H1	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	128	Hallway H1	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	129	Room 183 (Girls CR)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	129	Room 183 (Girls CR)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	130	Room 185	No	No	FL	VFT	7	N/D	-	-	40-B5-12B	-	-	-	-	-	-
1	130	Room 185	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	130	Room 185	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	130	Room 185	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-	-
1	130A	Room 185 A	No	No	FL	VFT	7	N/D	-	-	40-B5-12AC	-	-	-	-	-	-
1	130A	Room 185 A	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	V/C:40-B5-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile
1	130A	Room 185 A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-	-
1	130A	Room 185 A	No														




STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY																	
RF: Roof WN: Window FL: Floor CL: Ceiling WL: Wall DK: Deck			BUI: Beams/Joists CB: Ceiling Board PI: Pipe DT: Duct BL: Bolter MC: Mechanical			A: All occupants of the facility B: Maintenance staff without a ladder C: Maintenance staff with a ladder, exposed to view without moving building components D: Maintenance staff with a ladder, concealed from view by building components E: No access without demolition or removal of fixed building components or systems			ACM: Asbestos Containing Material CT: Ceiling Tile Analyzed DJC: Drywall Joint Compound FTG: Filling LF: Linear Felt MA: Mastic PCP: Pipe Insulation-Capstone			N/A: Not Applicable N/A/NZ: Not Analyzed ND: None Detected PI/AC: Pipe Insulation - Aircell PI-PC: Pipe Insulation-Pairing Cement N/A: Mastic			PL: Plaster RM: Roofing Materials SFP: Sprayed Fireproofing SF: Square Feet TF: Texture Finish			TB: Transit Board TP: Transit Pipe VI: Vermiculite Insulation VFT: Vinyl Floor Tile			VSF: Vinyl Sheet Flooring VC: Veneer/Carpeting or Other Sampled Material WC: Window Caulking		
						CONDITION			G: Good F: Fair P: Poor														
Floor #	Room #	Room name	Has ACM	Frishie	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes						
1	134	Room 187	No	No	FL	VFT	9	NID	-	-	V/C:40-BS-14C	-	-	-	-	-	-						
1	134	Room 187	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	40-BS-03D	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	134	Room 187	No	No	CL	CT	1	NID	-	-	40-BS-07C	-	-	-	-	-	-						
1	134	Room 187	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	135	Room 188	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	40-BS-03E	-	-	C	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	135	Room 188	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	135	Room 188	No	No	FL	VFT	11	Chrysotile	0	-	VIC 40-BS-17A	-	-	-	-	-	-	2018 Survey/Replaced with non-ACM: 2017 July 2017-tiles chrysotile, consider removing entire floor.					
1	136	Stairs 4	No	Yes	WL	TF		NID	-	-	V/C: 40-BS-01	-	-	-	-	-	-						
1	136	Stairs 4	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	136	Stairs 4	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	137	Room 188 A	No	No	FL	VFT	2	NID	-	-	V/C: 40-BS-06	-	-	-	-	-	-						
1	137	Room 188 A	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	137	Room 188 A	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	138	Room 190	No	No	FL	VFT	2	NID	-	-	V/C: 40-BS-06	-	-	-	-	-	-						
1	138	Room 190	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	138	Room 190	No	No	CL	CT	2	NID	-	-	V/C: 40-BS-16	-	-	-	-	-	-						
1	138	Room 190	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	139	Room 191	No	No	FL	VFT	2	NID	-	-	V/C: 40-BS-06	-	-	-	-	-	-						
1	139	Room 191	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	139	Room 191	No	No	CL	CT	2	NID	-	-	V/C: 40-BS-16	-	-	-	-	-	-						
1	139	Room 191	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	140	Hallway H6	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	140	Hallway H6	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	140	Hallway H6	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	141	Room 193	No	No	FL	VFT	10	NID	-	-	40-BS-15C	-	-	-	-	-	-						
1	141	Room 193	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	141	Room 193	No	No	CL	CT	2	NID	-	-	40-BS-16C	-	-	-	-	-	-						
1	141	Room 193	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	142	Room 195	No	No	FL	VFT	10	NID	-	-	40-BS-15A	-	-	-	-	-	-						
1	142	Room 195	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	142	Room 195	No	No	CL	CT	2	NID	-	-	40-BS-16B	-	-	-	-	-	-						
1	142	Room 195	No	No	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	143	Stairs 5	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	143	Stairs 5	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	144	Room 194	No	No	FL	VFT	10	NID	-	-	40-BS-15B	-	-	-	-	-	-						
1	144	Room 194	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	144	Room 194	No	No	CL	CT	2	NID	-	-	40-BS-16A	-	-	-	-	-	-						
1	144	Room 194	No	No	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	145	Room 192	No	No	FL	VFT	12	NID	-	-	40-BS-18A	-	-	-	-	-	-						
1	145	Room 192	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	145	Room 192	No	No	CL	CT	2	NID	-	-	V/C: 40-BS-16	-	-	-	-	-	-						
1	145	Room 192	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	146	Room 189	No	No	FL	VFT	12	NID	-	-	40-BS-18B,C	-	-	-	-	-	-						
1	146	Room 189	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	146	Room 189	No	No	CL	CT	2	NID	-	-	V/C: 40-BS-16	-	-	-	-	-	-						
1	146	Room 189	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	147	Hallway H7	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	147	Hallway H7	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	147	Hallway H7	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	148	Room 197 (Girls WR)	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	148	Room 197 (Girls WR)	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	149	Room 196 (Boys WR)	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	149	Room 196 (Boys WR)	No	No	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	150	Room 138	No	No	FL	VFT	1	NID	-	-	V/C: 40-BS-05	-	-	-	-	-	-						
1	150	Room 138	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	150	Room 138	No	No	CL	CT	1	None-Detected	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	150	Room 138	Yes	No	ST	SFP		None-Detected	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	151	Hallway H8	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	151	Hallway H8	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	151	Hallway H8	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	152	Room 136	No	No	FL	VFT	4	NID	-	-	V/C: 40-BS-09A,B,C	-	-	-	-	-	-	vft-4 was not observed during this reassessment					
1	152	Room 136	No	No	FL	VFT	1	NID	-	-	V/C: 40-BS-05	-	-	-	-	-	-						
1	152	Room 136	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	152	Room 136	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	152	Room 136	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	153	Room 132	No	No	FL	VFT	1	NID	-	-	V/C: 40-BS-05	-	-	-	-	-	-						
1	153	Room 132	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	153	Room 132	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	153	Room 132	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	154	Room 128	No	No	FL	VFT	1	NID	-	-	40-BS-05C	-	-	-	-	-	-						
1	154	Room 128	No	Yes	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile					
1	154	Room 128	No	No	CL	CT	1	NID	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	154	Room 128	No	Yes	ST	SFP		NID	-	-	V/C: 40-BS-21	-	-	-	-	-							



STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY																	
RF: Roof WN: Window FL: Floor CL: Ceiling WL: Wall DK: Deck			B/J: Beams/Joists CB: Chalkboard PI: Pipe DT: Duct BL: Bolter MC: Mechanical			A: All occupants of the facility B: Maintenance staff without a ladder C: Maintenance staff with a ladder, exposed to view without moving building components D: Maintenance staff with a ladder, concealed from view by building components E: No access without demolition or removal of fixed building components or systems			ACM: Asbestos Containing Material CT: Ceiling Tile DJC: Drywall Joint Compound FTG: Fitting LF: Linear Feet MA: Mastic CONDITION: G: Good F: Fair P: Poor			N/A: Not Applicable N/A/NZ: Not Analyzed ND: None Detected PI/AC: Pipe Insulation - Aircell PI-PC: Pipe Insulation-Pairing Cement PI-CP: Pipe Insulation-Capsule			PL: Plaster RM: Roofing Materials SFP: Sprayed Fireproofing SF: Square Feet TF: Texture Finish			TB: Transite Board TP: Transite Pipe VI: Vermiculite Insulation VFT: Vinyl Floor Tile			VSF: Vinyl Sheet Flooring VC: Visually Consistent w/ Other Sampled Material WC: Window Caulking		
Floor #	Room #	Room name	Has ACM	Frishie	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes						
1	160	Room 121	No	Yes	ST	SFP		N/D	-	-	V/C:40-B5-21			-									
1	161	Room 119	No	No	FL	VFT	1	N/D	-	-	N/D			-									
1	161	Room 119	No	Yes	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	161	Room 119	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	162	Room 198 (Storage)	No	No	FL	VFT	5	N/D	-	-	V/C:40-B5-10	-	-	-	-	-							
1	162	Room 198 (Storage)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	162	Room 198 (Storage)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	164	Room 114 (Staff Room)	No	No	FL	VFT	1	N/D	-	-	40-B5-03B	-	-	-	-	-							
1	164	Room 114 (Staff Room)	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	164	Room 114 (Staff Room)	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	164	Room 114 (Staff Room)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	165	Room 116 (Backstage)	No	No	FL	VFT	5	N/D	-	-	V/C:40-B5-10	-	-	-	-	-							
1	165	Room 116 (Backstage)	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	165	Room 116 (Backstage)	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	165	Room 116 (Backstage)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	165A	Room 193 A	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-							
1	165A	Room 193 A	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	165A	Room 193 A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	166	Room 115 (Stage)	No	No	FL	VFT	12	N/D	-	-	V/C:40-B5-18	-	-	-	-	-							
1	166	Room 115 (Stage)	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	167	Room 113 Cafeteria	No	No	FL	VFT	14	N/D	-	-	40-B5-20A,B,C	-	-	-	-	-							
1	167	Room 113 Cafeteria	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	167	Room 113 Cafeteria	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	168	Room 117 C	No	No	FL	VSF	2	N/D	-	-	40-B5-04A	-	-	-	-	-							
1	168	Room 117 C	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	168	Room 117 C	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	168	Room 117 C	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	168A	Room 117 B	No	No	FL	VSF	2	N/D	-	-	40-B5-04C	-	-	-	-	-							
1	168A	Room 117 B	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	168A	Room 117 B	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	168A	Room 117 B	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	169	Room 199	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	169	Room 199	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	170	Room 199 A	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	170	Room 199 A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	171	Room 117 A	No	No	FL	VSF	2	N/D	-	-	40-B5-04C	-	-	-	-	-							
1	171	Room 117 A	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	171	Room 117 A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	171	Room 117 A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	172	Room 112	No	No	FL	VFT	6	N/D	-	-	V/C:40-B5-11	-	-	-	-	-							
1	172	Room 112	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	172	Room 112	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	172	Room 112	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	172A	Room 112A	No	No	FL	VFT	6	N/D	-	-	V/C:40-B5-11	-	-	-	-	-							
1	172A	Room 112A	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	172A	Room 112A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	172A	Room 112A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	173	Room 111 (Storage)	No	No	FL	VFT	5	N/D	-	-	V/C:40-B5-10	-	-	-	-	-							
1	173	Room 111 (Storage)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	173	Room 111 (Storage)	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	174	Room 109	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-							
1	174	Room 109	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	174	Room 109	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	174	Room 109	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	174A	Room 109 A	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-							
1	174A	Room 109 A	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	174A	Room 109 A	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	174A	Room 109 A	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	174B	Room 109 B	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-							
1	174B	Room 109 B	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	174B	Room 109 B	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	174B	Room 109 B	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	174C	Room 109 C	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-							
1	174C	Room 109 C	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	174C	Room 109 C	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	174C	Room 109 C	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	174D	Room 109 D	No	No	FL	VFT	1	N/D	-	-	V/C:40-B5-05	-	-	-	-	-							
1	174D	Room 109 D	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	174D	Room 109 D	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	174D	Room 109 D	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	175	Room 137	-	-	-	-	-	-	-	-	-	-	-	-	-	-	ACM and/orPACM not observed						
1	175A	Room 137 (Gym Storage)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	ACM and/orPACM not observed						
1	176	Hallway H11	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	176	Hallway H11	No	No	CL	CT	1	N/D	-	-	V/C:40-B5-07	-	-	-	-	-							
1	176	Hallway H11	No	Yes	ST	SFP	-	N/D	-	-	V/C:40-B5-21	-	-	-	-	-							
1	177	Room 145 (Library)	Yes	No	WL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	177	Room 145 (Library)	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	-	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	177	Room 145 (Library)	No	Yes	ST	SFP	-	N/D	-	-													



STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY																	
RF: Roof WH: Window FL: Floor CL: Ceiling WL: Wall DK: Deck			B.U: Beams/Joints B: Chalkboard P: Pipe DT: Duct BL: Boiler MC: Mechanical			A: All occupants of the facility B: Maintenance staff without a ladder C: Maintenance staff with a ladder, exposed to view without moving building components D: Maintenance staff with a ladder, concealed from view by building components E: No access without demolition or removal of fixed building components or systems			ACM: Asbestos Containing Material CT: Ceiling Tile DJC: Drywall Joint Compound FTG: Fitting LF: Linear Feet Mst: Mastic CONDITION: G: Good F: Fair P: Poor			N/A: Not Applicable N/A/NZ: Not Analyzed N/D: None Detected PI/AC: Pipe Insulation - Aircell PI/PC: Pipe Insulation-Parging Cement PI/CP: Pipe Insulation-Capsule			PL: Plaster RM: Roofing Materials SFP: Sprayed Fireproofing SF: Square Feet TF: Texture Finish			TB: Transite Board TP: Transite Pipe VI: Vermiculite Insulation VFT: Vinyl Floor Tile			VSP: Vinyl Sheet Flooring VIC: Visually Consistent w/ Other Sampled Material WC: Window Caulking		
Floor #	Room #	Room name	Has ACM	Frishie	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes						
1	181	Room 118 (I B Coordinator)	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	181	Room 118 (I B Coordinator)	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	182	Room 120 (Business EC)	No	No	FL	VFT	2	N/D	-	-	40-BS-06C	-	-	-	-	-	-						
1	182	Room 120 (Business EC)	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	-						
1	182	Room 120 (Business EC)	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	182	Room 120 (Business EC)	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	182A	Room 120 A	No	No	FL	VFT	2	N/D	-	-	40-BS-06B	-	-	-	-	-	-						
1	182A	Room 120 A	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	182A	Room 120 A	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	182A	Room 120 A	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	183	Room 129	No	No	FL	VFT	1	N/D	-	-	V/C: 40-BS-06	-	-	-	-	-	-						
1	183	Room 129	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	183	Room 129	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	183	Room 129	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	184	Room 130	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11	-	-	-	-	-	-						
1	184	Room 130	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	184	Room 130	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	184	Room 130	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	185	Room 134	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11	-	-	-	-	-	-						
1	185	Room 134	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	185	Room 134	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	185	Room 134	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	186	Room 184	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	186	Room 184	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	186	Room 184	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	187	Room 181	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	187	Room 181	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	187	Room 181	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	187	Room 181	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	188	Room 180	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	188	Room 180	Yes	No	CL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	188	Room 180	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	188A	Room 180 A	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	188A	Room 180 A	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	188A	Room 180 A	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	188B	Room 180 B	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	188B	Room 180 B	Yes	No	CL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	188B	Room 180 B	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	188C	Room 180 C	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	188C	Room 180 C	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	188C	Room 180 C	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	189	Room 179	No	No	FL	VFT	8	N/D	-	-	40-BS-13A,B,C	-	-	-	-	-	-						
1	189	Room 179	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	189	Room 179	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	190	Room 175	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	190	Room 175	Yes	No	CL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	190	Room 175	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	191	Room 173B	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	191	Room 173B	Yes	No	CL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	191	Room 173B	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	191A	Room 173A	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	191A	Room 173A	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	191A	Room 173A	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	191B	Room 173C	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13	-	-	-	-	-	-						
1	191B	Room 173C	Yes	No	CL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	C	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	191B	Room 173C	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	192	Room 171	Yes	No	CL	DJC	-	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	192	Room 171	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	192	Room 171	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	192	Room 171	Yes	No	FL	MA	-	2% Chrysotile	900 SF	G	18778-S01A	-	-	E	-	-	Black mastic, present below VFT						
1	193	Room 169	No	No	FL	VFT	13	N/D	-	-	40-BS-19A	-	-	-	-	-	-						
1	193	Room 169	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	40-BS-03F	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	193	Room 169	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	193	Room 169	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	193A	Room 169 A	No	No	FL	VFT	13	N/D	-	-	40-BS-19B,C	-	-	-	-	-	-						
1	193A	Room 169 A	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	40-BS-03F	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	193A	Room 169 A	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	193A	Room 169 A	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	40-BS-03F	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	194	Room 156	No	No	FL	VFT	3	N/D	-	-	40-BS-08A,B,C	-	-	-	-	-	-						
1	194	Room 156	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	40-BS-03F	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	194	Room 156	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07	-	-	-	-	-	-						
1	194	Room 156	No	Yes	ST	SFP	-	N/D	-	-	V/C: 40-BS-21	-	-	-	-	-	-						
1	195	Room 155	No	No	FL	VFT	13	N/D	-	-	40-BS-19 B,C	-	-	-	-	-	-						
1	195	Room 155	Yes	No	WL	DJC	1	0.75% -1% Chrysotile	1	G	V/C: 40-BS-03	-	-	A	-	-	Samples E& F confirmed to contain 0.75%-1% Chrysotile						
1	195	Room 155	No	No	CL	CT	1	N/D	-	-	40-BS-07A	-	-	-	-	-	-						
1	195	Room 155	No	Yes	ST	SFP																	





STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY														
RF: Roof	B0: Beams/Joists		A: All occupants of the facility			ACM: Asbestos Containing Material		N/A: Not Applicable			PL: Plaster		TB: Transite Board			VSP: Vinyl Sheet Flooring				
WN: Window	C: Checkboard		B: Maintenance staff without a ladder			CT: Ceiling Tile		N/A/NZ: Not Analyzed			RM: Roofing Materials		TP: Transite Pipe			VC: Visually Consistent w/ Other Sampled Material				
FL: Floor	PI: Pipe		C: Maintenance staff with a ladder, exposed to view without moving building components			DJC: Drywall Joint Compound		ND: None Detected			SFP: Sprayed Fireproofing		VI: Vermiculite Insulation			WC: Window Caulking				
CL: Ceiling	TD: Duct		D: Maintenance staff with a ladder, concealed from view by building components			FTG: Fitting		PI/AC: Pipe Insulation - Aircell			SF: Square Feet		VF: Vinyl Floor Tile							
WL: Wall	BL: Boiler		E: No access without demolition or removal of fixed building components or systems			LF: Linear Feet		PI/PC: Pipe Insulation-Pairing Cement			TF: Texture Finish									
DK: Deck	MC: Mechanical					M&M: Mastic														
						CONDITION	G: Good F: Fair P: Poor													
Floor #	Room #	Room name	Has ACM	Prohibe	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes			
2	233	Room 246	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	233	Room 246	No	No	FL	CT	1	ND	-	-	V/C: 40-BS-07			-						
2	233	Room 246	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	234	Stair 4	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	234	Stair 4	No	No	WL	TF	2	ND	-	-	40-BS-01 E			-						
2	234	Stair 4	No	No	CL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	234	Stair 4	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	235	Room 235 (Janitor Room)	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			C			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	235	Room 235 (Janitor Room)	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	236	Hallway- H14	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	236	Hallway- H14	No	No	CL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	236	Hallway- H14	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	238	Hallway- H15	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	238	Hallway- H15	No	No	CL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	238	Hallway- H15	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	239	Room 226	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	239	Room 226	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samoles E& F confirmed to contain 0.75%-1% Chrysotile			
2	239	Room 226	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	239	Room 226	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	240	Room 228	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			C			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	240	Room 228	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	241	Room 229	Yes	No	CL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			C			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	241	Room 229	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	242	Room 230	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	242	Room 230	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	242	Room 230	No	No	FL	CT	2	ND	-	-	V/C:40-BS-16			-						
2	242	Room 230	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	243	Room 232	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	243	Room 232	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	243	Room 232	No	No	FL	CT	2	ND	-	-	V/C:40-BS-16			-						
2	243	Room 232	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	244	Room 234	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	244	Room 234	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	244	Room 234	No	No	FL	CT	2	ND	-	-	V/C:40-BS-16			-						
2	244	Room 234	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	245	Stair 5	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	245	Stair 5	No	No	CL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	245	Stair 5	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	246	Room 233	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	246	Room 233	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samoles E& F confirmed to contain 0.75%-1% Chrysotile			
2	246	Room 233	No	No	FL	CT	2	ND	-	-	V/C:40-BS-16			-						
2	246	Room 233	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	247	Room 231	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	247	Room 231	No	No	FL	CT	2	ND	-	-	V/C:40-BS-16			-						
2	247	Room 231	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	247	Room 231	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A						
2	248	Room 227	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	248	Room 227	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	248	Room 227	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	248	Room 227	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	249	Room 225	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	249	Room 225	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	249	Room 225	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	249	Room 225	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	250	Room 224	No	No	FL	VFT	2	ND	-	-	V/C:40-BS-06			-						
2	250	Room 224	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	250	Room 224	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	250	Room 224	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	251	Room 223	No	No	FL	VFT	1	ND	-	-	V/C:40-BS-06			-						
2	251	Room 223	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	251	Room 223	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	251	Room 223	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	252	Hallway H13	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	252	Hallway H13	No	No	CL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	252	Hallway H13	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	253	Room 221	No	No	FL	VFT	1	ND	-	-	V/C:40-BS-06			-						
2	253	Room 221	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	253	Room 221	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	253	Room 221	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	254	Room 219	No	No	FL	VFT	1	ND	-	-	V/C:40-BS-06			-						
2	254	Room 219	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	254	Room 219	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	254	Room 219	No	No	ST	SFP		ND	-	-	V/C: 40-BS-21			-						
2	255	Room 218	No	No	FL	VFT	1	ND	-	-	V/C:40-BS-06			-						
2	255	Room 218	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C:40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile			
2	255	Room 218	No	No	FL	CT	1	ND	-	-	V/C:40-BS-07			-						
2	255	Room 218	No	No	ST	SFP														



STRUCTURAL ELEMENT			ACCESSIBILITY			TERMINOLOGY											
RF: Roof	B/J: Beams/Joints	A: All occupants of the facility	ACM: Asbestos Containing Material	N/A: Not Applicable	PL: Plaster												
WN: Window	CB: Chalkboard	B: Maintenance staff without a ladder	N/A/NZ: Not Analyzed	RM: Roofing Materials	TP: Transite Pipe												
FL: Floor	PI: Pipe	C: Maintenance staff with a ladder, exposed to view without moving building components	PIAC: Pipe Insulation - Aircell	SFP: Sprayed Fireproofing	VI: Vermiculite Insulation												
CL: Ceiling	DT: Duct	D: Maintenance staff with a ladder, concealed from view by building components	FTG: Fitting	SF: Square Feet	VFT: Vinyl Floor Tile												
WL: Wall	BL: Boiler	E: No access without demolition or removal of fixed building components or systems	LF: Linear Feet	PI-PC: Pipe Insulation-Parging Cement	TF: Texture Finish												
DK: Deck	MC: Mechanical		ML: Mastic	PI-GP: Pipe Insulation-Capsulate													
			CONDITION G: Good F: Fair P: Poor														
Floor #	Room #	Room name	Has ACM	Frishie	Struct. Elem.	Application	Material	Type	Total Qty	Condition	Sample #	Action	Ref #	Comments 1	Comments 2	Comments 3	Notes
2	261	Room 217	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	261	Room 217	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	261	Room 217	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	262	Room 220	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	262	Room 220	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	262	Room 220	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	262	Room 220	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	263	Room 222	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	263	Room 222	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	263	Room 222	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	263	Room 222	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	264	Room 245	No	No	FL	VFT	8	N/D	-	-	V/C: 40-BS-13			-			
2	264	Room 245	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	264	Room 245	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	264	Room 245	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	265	Room 244	No	No	FL	VFT	11	2% Chrysotile	-	-	V/C: 40-BS-17			-			Removed
2	265	Room 244	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	265	Room 244	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	265	Room 244	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	266	Room 243	No	No	FL	VFT	1	N/D	-	-	V/C: 40-BS-05			-			
2	266	Room 243	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	266	Room 243	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	266	Room 243	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	267	Room 242	No	No	FL	VFT	1	N/D	-	-	V/C: 40-BS-05			-			
2	267	Room 242	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	267	Room 242	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	267	Room 242	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	268	Room 241	No	No	FL	VFT	1	N/D	-	-	V/C: 40-BS-05			-			
2	268	Room 241	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	268	Room 241	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	268	Room 241	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	269	Hallway H21	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	269	Hallway H21	No	No	CL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	269	Hallway H21	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	270	Room 248	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	270	Room 248	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	270	Room 248	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	270	Room 248	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	271	Room 252	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	271	Room 252	No	No	CL	CT	2	N/D	-	-	V/C: 40-BS-16			-			
2	271	Room 252	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	272	Room 255 (Mechanical Rm)	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	273	Room 256	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	273	Room 256	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	273	Room 256	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	273	Room 256	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	273A	Room 256 A	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	273A	Room 256 A	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	273A	Room 256 A	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	273A	Room 256 A	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	274	Room 258	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	274	Room 258	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	274	Room 258	No	No	FL	CT	1	N/D	-	-	V/C: 40-BS-07			-			
2	274	Room 258	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
2	274A	Room 262	No	No	FL	VFT	6	N/D	-	-	V/C: 40-BS-11			-			
2	274A	Room 262	Yes	No	WL	DJC		0.75% -1% Chrysotile	1	G	V/C: 40-BS-03			A			Samples E& F confirmed to contain 0.75%-1% Chrysotile
2	274A	Room 262	No	No	CL	CT	2	N/D	-	-	V/C: 40-BS-16			-			
2	274A	Room 262	No	No	ST	SFP		N/D	-	-	V/C: 40-BS-21			-			
NA		EXTERIOR	No	No	RF	RM	N/A	ACM ASSUMED	1	G	NS			C			sample prior to renovation
NA		EXTERIOR	No	No	WN	WC	N/A	ACM ASSUMED	1	G	NS			A, C			sample prior to renovation
NA		EXTERIOR	Suspect	No	WN	TB	N/A	ACM ASSUMED	1	G	NS			A, C			sample prior to renovation

APPENDIX II

DRAWINGS



Please Note:
Drywall Joint Compound (DJC) has been identified as ASBESTOS CONTAINING throughout the building.

Asbestos-containing transite board (TB) is suspected to be present on the building exterior.

Black mastic (MA) associated with vinyl floor tiles has been identified as ASBESTOS CONTAINING throughout the building.

LEGEND

12578-48-01A

ECO H Sample Locations

01-BS-01A

Jacques Whitford Sample Locations

#

Ebase Number

CONFIRMED ACM

SYMBOL

DESCRIPTION

Friable Asbestos-Containing Material

Non-Friable Asbestos-Containing Material

VFT

Vinyl Floor Tile (Non-Friable Asbestos-Containing Material)

TP

Transite Pipe (Non-Friable Asbestos-Containing Material)

NOTE

Drywall Joint Compound

NOTE

Transite Board

NOTE

Mastic

For Detailed Information as to Location, Type, Quantity, Condition and Access to ACM, Please Refer to the Room-by-Room Sheets Provided in the Report.

I.E. Weldon Secondary School

24 Weldon Road
Lindsay, Ontario

Second Floor Plan

Asbestos Materials Re-Assessment Survey

CLIENT: Trillium Lakelands District School Board

PROJECT NUMBER: 21700-48

DATE: September 2024

DRW BY: S. Knight

SCALE: Not to Scale

CHK BY: K. Prosser

MAPLE ENVIRONMENTAL INC.

ENVIRONMENT, HEALTH & SAFETY CONSULTANTS



NOTE: DAYCARE IS NO LONGER PART OF THE FACILITY

Please Note:
Drywall Joint Compound (DJC) has been identified as ASBESTOS CONTAINING throughout the building.

Asbestos-containing transite board (TB) is suspected to be present on the building exterior.

Black mastic (MA) associated with vinyl floor tiles has been identified as ASBESTOS CONTAINING throughout the building

LEGEND		
<div>12578-48-01A</div>	ECOH Sample Locations	
<div>01-BS-01A</div>	Jacques Whitford Sample Locations	
<div>#</div>	Ebase Number	
CONFIRMED ACM		
SYMBOL	DESCRIPTION	
<div></div>	Friable Asbestos-Containing Material	
<div></div>	Non-Friable Asbestos-Containing Material	
<div>VFT</div>	Vinyl Floor Tile (Non-Friable Asbestos-Containing Material)	
<div>TP</div>	Transite Pipe (Non-Friable Asbestos-Containing Material)	
NOTE	Drywall Joint Compound	
NOTE	Transite Board	
NOTE	Mastic	
For Detailed Information as to Location, Type, Quantity, Condition and Access to ACM, Please Refer to the Room-by-Room Sheets Provided in the Report.		
I.E. Weldon Secondary School		
24 Weldon Road Lindsay, Ontario		
Daycare - First Floor Plan		
Asbestos Materials Re-Assessment Survey		
CLIENT: Trillium Lakelands District School Board		
PROJECT NUMBER: 21700-48	DATE: September 2024	DRW BY: S. Knight
	SCALE: Not to Scale	CHK BY: K. Prosser
<div><div></div><div>MAPLE ENVIRONMENTAL INC.</div><div>ENVIRONMENT, HEALTH & SAFETY CONSULTANTS</div></div>		

APPENDIX III

POTENTIAL ASBESTOS-CONTAINING MATERIAL
IDENTIFICATION SHEET

APPENDIX III - POTENTIAL ASBESTOS-CONTAINING MATERIALS INFORMATION SHEET

<i>MIN</i>	<i>Material</i>	<i>Material Description</i>	<i>Size</i>	<i>Sample Number</i>	<i>Sample Location</i>	<i>Asbestos Containing</i>
VFT-1	Vinyl Floor Tiles	White with blue smears	12 x 12	40-BS-05 A,B,C	Room 153C,114,128	None
VFT-2	Vinyl Floor Tiles	White with black streaks	12 x 12	40-BS-06 A,B,C	Room 118,120,120A	None
VFT-3	Vinyl Floor Tiles	Black	12 x 12	40-BS-08 A,B,C	Room 156	None
VFT-4	Vinyl Floor Tiles	White with maroon streaks	12 x 12	40-BS-09 A,B,C	Room 127	0.5% Chrysotiles
VFT-5	Vinyl Floor Tiles	Green	12 x 12	40-BS-10 A,B,C	Room 126,168	None
VFT-6	Vinyl Floor Tiles	Crean with brown smears	12 x 12	40-BS-11 A,B,C	Room 112,155B,174	None
VFT-7	Vinyl Floor Tiles	Grey with white smears	12 x 12	40-BS-12 A,B,C	ROOM 185-185A	None
VFT-8	Vinyl Floor Tiles	Green with white smears	12 x 12	40-BS-13 A,B,C	Room 179	None
VFT-9	Vinyl Floor Tiles	Beige with purple smears	12 x 12	40-BS-14 A,B,C	Room 186,186A &186B	None
VFT-10	Vinyl Floor Tiles	White with grey streaks	12 x 12	40-BS-15 A,B,C	Room 195,194 &193	None
VFT-11	Vinyl Floor Tiles	Beige with maroon streaks	12 x 12	40-BS-17 A,B,C	Room 142,171 & 188	2% Chrysotiles
VFT-12	Vinyl Floor Tiles	Crean with grey streaks	12 x 12	40-BS-18 A,B,C	Room 192,189Ws & 189 Ns	None
VFT-13	Vinyl Floor Tiles	Light green with grey & white smears	9 x 9	40-BS-19 A,B,C	Room 169 & 169A	None
VFT-14	Vinyl Floor Tiles	Light greY with grey with brown streaks	9 x 9	40-BS-20 A,B,C	Cafeteria	None
CT-1	Ceiling Tiles	Medium fissure pinhole pattern	2x4	40-BS-07 A,B,C	Hallway 5, Room 155 &187	None
CT-2	Ceiling Tiles	Very small fissure pinhole pattern	2x4	40-BS-16 A,B,C	Room 193,194 &195	None
VSF-1	Vinyl Sheet Floor	Checkered	N/A	40-BS-02 A,B,C	Daycare Staffroom	None
VSF-2	Vinyl Sheet Floor	Brown with black dots	N/A	40-BS-04 A,B,C	Room 117 A,B & C	None